



Date Prepared: 23APR20

Date Revised: 15OCT20

Version: 3.0

TDS – EcoSoya PillarBlend

Information

Product Description

EcoSoya PillarBlend is formulated for use in the manufacture of pillar candles.

Physical Properties

Test	Method	Specification	Typical Value
Congealing Point, °C	ASTM D938	48 – 52	50
Viscosity @ 100°C, cSt	ASTM D445	8 – 11	9.5
Penetration @ 25°C, dmm	BS 1426	15 – 25	20
Colour	ASTM D1500	1.0 Max	0.6
Colour	Visual	Off White	Off White

Statement

- Formulated from materials whose refining history is fully traceable.
- Due to the prevalence of genetically modified soybean crop in the market we are unable to guarantee entirely non-GMO sources but we aim to source non-GMO wherever possible.
- Does not contain residual solvents as per guidelines CPMP/ICH283/95.
- Has not been tested on animals by ourselves or on our behalf.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users must make their own tests to determine the suitability of these products for their own particular purposes. The company makes no warranty of any kind, expressed or implied, including those of merchantability or fitness for a particular purpose, other than that the material conforms to its applicable current Standard Specifications.